196 Paterson Ave, 2nd Floor
East Rutherford, NJ 07073
Tel: 201-299-4499 Fax: 201-335-5909

"Your #1 Source for Chemical Foaming Agents"

Foamazol™ 12

A Foaming Rotational Molding Compound

PRODUCT DATA

Application	Intended for use in foamed rotational molding applications.
Characteristics:	Endothermic Decomposition
Regulatory Status:	All raw materials are GRAS (generally recognized as safe)
Physical Appearance:	Supplied as white pellets.

Technical Data

Decomposition:	130-145°C (266-293°F)
Processing Recommendations:	Maximum gas yields are achieved when processing temperatures of 175-200°C (347-392ºF) are reached

Usage Levels

Injection Molding:	Not recommended for use.
Extrusion:	Not recommended for use.
Rotational Molding:	100%

The information and recommendations made herein are based on the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of this product, and purchasers should make their own tests and evaluation to determine the suitability of this product in their application. Nothing herein is to be construed as a recommendation to use or as a license to operate under or to infringe any existing patents.